

# Serge Ferrari Flexlight

Classic 602 & 602 Opaque

**Main applications**  
Industrial tents



## Major advantages

- Good ratio of weight and mechanical resistance for standard applications
- Compliant with worldwide fire norms
- Easy to weld
- Exceptional dimensional stability due to Precontraint technology

# Serge Ferrari Flexlight

## Classic 602 & 602 Opaque

### 4 colours

#### Translucent



250 - 267 cm


602-8100



250 - 267 cm

602-8341

#### Opaque



250 - 267 cm

602-8503



250 - 267 cm

602-50020

### Technical specifications

	Flexlight Classic 602	Flexlight Classic 602 Opaque
Weight	650 g/m <sup>2</sup> - EN ISO 2286-2	750 g/m <sup>2</sup> - EN ISO 2286-2
Width	250 - 267 cm	250 - 267 cm
Standard format length	50 lm - 300 lm	rolls: 50 lm - jumbo rolls: 300 lm
Tensile strength (warp/weft)	250/250 daN / 5 cm - EN ISO 1421	250/250 daN / 5 cm - EN ISO 1421
Tear strength (warp/weft)	25 / 25 daN - DIN 53.363	25 / 25 daN - DIN 53.363
Adhesion	9 daN / 5 cm - EN ISO 2411	9 daN / 5 cm - EN ISO 2411
Yarn	Standard	Standard
Coating	Standard	Standard
Finish	Acrylic both side	Acrylic both side
Flame retardancy	<b>B,s2,d0</b> ; EN ISO 13501-1 — <b>M2</b> NF P92-507 — <b>M2</b> UNE 23727-90; <b>B1</b> DIN 4102-1 BS 7837 — ONORM A3800 — NFPA 701 <b>Method 1</b> — NFPA 701 <b>Method 2</b> — ASTM E662 T19 CSFM — ASNZS <b>1530.2</b> — ASNZS <b>1530.3</b> — T2 EN 15619 — ISO 4675 <b>FAR JAR</b> 25-853-855 — <b>NF</b> EN ISO 846	<b>B,s2,d0</b> ; EN ISO 13501-1 — <b>M2</b> NF P92-507 — <b>M2</b> UNE 23727-90; <b>B1</b> DIN 4102-1 BS 7837 — ONORM A3800 — NFPA 701 <b>Method 1</b> — NFPA 701 <b>Method 2</b> — ASTM E662 — T19 CSFM — ASNZS <b>1530.2</b> — ASNZS <b>1530.3</b>

**Preconstraint®**  
Technology

**5-year**  
warranty  
Australia & NZ  
Refer warranty doc.

